



## BC SEAL BAND

Article Code see DDT

Date of issue 19.12.2017

Revision nr. 04

Page 1 of 2

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –  
[info@winklerchimica.com](mailto:info@winklerchimica.com) [www.winklerchimica.com](http://www.winklerchimica.com)

### DESCRIPTION

Self adhesive band based on butylic mastic covered with non-woven which allows the deformation of the product. The adhesive side is protected by peel off support.

### APPLICATION FIELDS

Sealing of wall-floor joints under tile or on existent tiled floors, before laying the new ones. The non-woven covering adapts to the support form and can be covered by tile adhesive or other covering, or paints. Joints waterproofing. Slits reparation in cement, fiber-cement or metal.

### SURFACES PREPARATION

Application surfaces must be clean, dry and free from dust.

### WARNINGS

Do not add any additive  
Do not use in case of damaged packaging.  
Do not expose to U.V. rays

### APPLICATION

Remove the protection, put the band on the support avoiding the formation of air bubbles between the butyl and the support.  
For joints superimpose the products of at least 5 cm.  
For sealing substrates subject to significant expansion, it is recommended to provide a method of application of BC SEAL BAND, suitable to withstand such tensions.  
Apply at temperatures between +5°C and +40°C.

### USEFUL ADVICES

Prior the application it is advisable to restore any irregularities on the surface, glue any detached tiles and check for hidden humidity to avoid the formation of vapor tensions.  
Avoid use when rainy weather is imminent and on wet surfaces.  
Cover the product within 24 hours, after its application.

### PACKAGING

1 roll per box – 80mm x 10m

#### Colour:

Non-woven: white

Butyl: grey

The information contained in this technical data sheet is to the best of our knowledge correct. However, by no means can it be considered a guarantee, as usage, working area and application of the product in accordance with the instructions given and their success in application is beyond our control and is dependent on a number of factors. We decline any responsibility for the improper use of the product as the application recommendations contained herein are to be considered as a general guideline. If at all in doubt, preliminary tests should be carried out. WINKLER S.r.l. reserves the right to modify and up-date said data sheets without prior notice. Clients are kindly requested to verify that they are in possession of the current edition.



## BC SEAL BAND

Article Code see DDT

Date of issue 19.12.2017

Revision nr. 04

Page 2 of 2

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –  
[info@winklerchimica.com](mailto:info@winklerchimica.com) [www.winklerchimica.com](http://www.winklerchimica.com)

### STORAGE

The product has 12 months stability from the production date if properly packed and not opened. Store in a ventilated room sheltered from dampness at temperatures between +5°C and +35°C.

### SAFETY INSTRUCTIONS

### PRECAUTIONS

For information about safety, user must refer to the most recent Safety Data Sheet, edited in accordance with the regulations in force, which contains physical, toxic and other data about the product in use.

### ECOLOGY

Do not through out the product and/or empty containers in the environment. Consult the most recent Safety Data Sheet for further information about disposals.

### TECHNICAL CHARACTERISTICS

Nature	Film type	100% polypropylene
	Compound type	Butyl rubber
Mass m <sup>2</sup>	D 45 1012	50 g/m <sup>2</sup>
Water-repellent		yes
Solids content by weight		100%
Drip resistance	Butyl at +5°C ISO 7390	< 3 mm
	Butyl at +70°C ISO 7390	< 3 mm
Reaction at -30°C	D421313	No detachment
Strain resistance	Perforated sheet warm method D455256	No strain
Peeling a 90°	On steel MEL 052	> 4 N/cm
Probe tack	ASTM D 2979	7,5 N
Waterproofing	EN 1928	Pass
Low temperature bending	EN 495-5	≤ - 40°C
Vapour transmission	EN 1931	μ 26176 ± 30%
Hit resistance	EN 12691	Met. B ≥ 100 mm
Break resistance	EN 12310	Long. ≥ 130 N
		Trans. ≥ 125 N
Tensile strenght at break	EN 12311	Long. ≥ 145 N/50 mm ≥ 100%
		Trans. ≥ 105 N/50 mm ≥ 100%
Temperature	Application temperature	+ 5°C < T < +40°C
	Hold break	- 30°C < T < +80°C

The information contained in this technical data sheet is to the best of our knowledge correct. However, by no means can it be considered a guarantee, as usage, working area and application of the product in accordance with the instructions given and their success in application is beyond our control and is dependent on a number of factors. We decline any responsibility for the improper use of the product as the application recommendations contained herein are to be considered as a general guideline. If at all in doubt, preliminary tests should be carried out. WINKLER S.r.l. reserves the right to modify and up-date said data sheets without prior notice. Clients are kindly requested to verify that they are in possession of the current edition.