



WINSTUCCO FLEX MEDIUM

Art. code see DDT

Date of issue 13.02.2017

Review nr. 02

Page 1 of 4

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

COMPLYING WITH THE UE LAW

EN 13888

CG2

CEMENT BASED MORTAR
FOR LEAKS

NATURE OF THE PRODUCT

Mono-component waterproofing grout with a low elastic module for applications on floors also subject to strong motions Developed in WINKLER Research & Development laboratories.

USE

The product is used to seal and waterproof leaks in floors, even if subject to strong movements, and also between tiles from 2 to 12 mm. The product is resistant to common detergents and to most aggressive alkaline solutions. It can be used both in interiors or exteriors.

PREPARATION OF SURFACES

Before starting with the filling ensure that the collocation's been well done and the tiles are well fixed. Make the filling respecting the waiting time of the chosen adhesive. Clean immediately the excess glue before it hardens.

RECOMMENDATIONS

- No additives nor cement required.
- Do not use if the container is damaged.
- Do not add water when the mixture starts to harden.
- Do not apply on asphalt or bitumen treated surfaces.

APPLICATION

To the best of our knowledge, the information contained in this prospectus are correct and accurate, but every recommendation and suggestion is given without any guarantees, as the using conditions are not under our direct control. It is advisable to always perform some preliminary tests.
Our company reserves the right to modify the products and the content of this document without any warning.
The present edition annuls and replaces any other previous edition.

IN CASE OF DOUBT PLEASE CONSULT OUR TECHNICAL SUPPORT



WINSTUCCO FLEX MEDIUM

Art. code see DDT

Date of issue 13.02.2017

Review nr. 02

Page 2 of 4

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

Mix well in order to obtain an homogeneous mixture free from lumps. The leaks must be clean, dry and free from brittles parts. It can be applied with spatula.

WARNINGS

Do not use the product to fill leaks bigger than 12mm, nor for filling expansion joints on surfaces which aren't perfectly dry or with backwater. Apply at temperatures between +5°C and + 35°C.

CONSUMPTION

400-700 g/m².

PACKAGING

5-25kgs bags.

STORAGE

If the product is stored in its unopened original packaging shelf-life is 12 months. Store at temperatures between +5°C and +35°C.

SAFETY STANDARDS

CAUTION

For information about safety standards, users must refer to the most recent Safety Sheet drafted in compliance with currently applicable Safety Standards, containing physical, toxicological and other data about the product used.

ECOLOGY

Dispose of the product and/or empty packaging in appropriate sites. For further information about waste disposal, see the most recent Safety Sheet.

To the best of our knowledge, the information contained in this prospectus are correct and accurate, but every recommendation and suggestion is given without any guarantees, as the using conditions are not under our direct control. It is advisable to always perform some preliminary tests.
Our company reserves the right to modify the products and the content of this document without any warning.
The present edition annuls and replaces any other previous edition.

IN CASE OF DOUBT PLEASE CONSULT OUR TECHNICAL SUPPORT



WINSTUCCO FLEX MEDIUM

Art. code see DDT

Date of issue 13.02.2017

Review nr. 02

Page 3 of 4

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

TECHNICAL DATA (average values)

WINSTUCCO FLEX meets the EN 13888 law (cementitious mortar for filling leaks) and the minimal requests on CG2 classification : WATER-REPELLENT EFFECT.

PRODUCT FOR PROFESSIONALS

PRODUCT DATA

Appearance:	powder
Colour:	White/grey
Mixture water:	20%
Mixture volume mass EN 1015/6 (Kg/m ³)	1660
Fire reaction 8EN 13501-1):	A 1
Thermal conductivity (EN 1745) (λ):	0,70 W/mk
Dampness resistance:	Good
Aging resistance	Good
Sodium chloride resistance	Good
Compression resistance after 28 days	Meets with EN 13888
CUSTOM CODE	38245090

Product in compliance with Directive 2003/53/EC

To the best of our knowledge, the information contained in this prospectus are correct and accurate, but every recommendation and suggestion is given without any guarantees, as the using conditions are not under our direct control. It is advisable to always perform some preliminary tests.
Our company reserves the right to modify the products and the content of this document without any warning.
The present edition annuls and replaces any other previous edition.

IN CASE OF DOUBT PLEASE CONSULT OUR TECHNICAL SUPPORT



WINSTUCCO FLEX MEDIUM

Art. code see DDT

Date of issue 13.02.2017

Review nr. 02

Page 4 of 4

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

To the best of our knowledge, the information contained in this prospectus are correct and accurate, but every recommendation and suggestion is given without any guarantees, as the using conditions are not under our direct control. It is advisable to always perform some preliminary tests.
Our company reserves the right to modify the products and the content of this document without any warning.
The present edition annuls and replaces any other previous edition.

IN CASE OF DOUBT PLEASE CONSULT OUR TECHNICAL SUPPORT