



ADEGUM LATEX

Art. Code DDT

Date of issue 15.03.2010

Review nr. 01

Page 1 of 2

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

DESCRIPTION

ADEGUM LATEX is an Adhesion Promoting for mortar and liquid mortar.

USAGE

ADEGUM LATEX makes the compounds highly adhesive, very pliable, elastic and waterproofing. It's use for adhesive liquid mortar construction, for the placement recover, restoring, renewal, plastering, cement rendering, and wherever excellent adhesion and resistance to weathering are required.

PHYSICAL / TECHNICAL PROPRIETIES

Appearance: liquid

Color: white

Specific Gravity @ 20°C (g/cm³) : 0,98

Solubility: water

Solids by Volume (%) : 28

Ph: 9

Elongation (%) : 1000

Mtf: + 5°C

SURFACE PREPARATION:

Ensure that surface is clean and in good repair. Surface must be free of dirt, residues, water repellent compounds, and other foreign matter. The surface must be wetted until refuse before applying the mortar / liquid mortar.

APPLICATIONS

The product is ready to use and it must be added in the mixing water.

CONSUMPTION

Liquid Mortar: 2,5 parts of cement, 1 part of ADEGUM LATEX, 1 part of water

Rough liquid mortar: 2,5 part of cement, 2 parts of sand, 1 part of ADEGUM LATEX – 1 part of water

Mortars: 10% based on the weight of the cement.

PRECAUTIONS:

The surface must be wetted until refuse before applying the mortar / liquid mortar, protect if necessary, in the first 24 hours fro direct sun radiation and from wind.

To the best of our knowledge, the information contained in this prospectus are correct and accurate, but every recommendation and suggestion is given without any guarantees, as the using conditions are not under our direct control. It is advisable to always perform some preliminary tests.
Our company reserves the right to modify the products and the content of this document without any warning.
The present edition annuls and replaces any other previous edition.

IN CASE OF DOUBT PLEASE CONSULT OUR TECHNICAL SUPPORT



ADEGUM LATEX

Art. Code DDT

Date of issue 15.03.2010

Review nr. 01

Page 2 of 2

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

PACKAGING

1 kg bottles

5, 10, 20 kg drums

STORAGE

The product has 12 months stability if properly stored in a cold dry place.

Limit temperatures of storage (+ 5 °C , + 35°C).

It's not frost resistance.

SAFETY INSTRUCTIONS

PRECAUTIONS

For information about safety, user must refer to the most recent Safety Data Sheet, edited in accordance with the regulations in force, which contains physical, toxic and other data about the product in use.

ECOLOGY

Do not through out the product and/or empty containers in the environment. Consult the most recent Safety Data Sheet for further information about disposals.

To the best of our knowledge, the information contained in this prospectus are correct and accurate, but every recommendation and suggestion is given without any guarantees, as the using conditions are not under our direct control. It is advisable to always perform some preliminary tests.
Our company reserves the right to modify the products and the content of this document without any warning.
The present edition annuls and replaces any other previous edition.

IN CASE OF DOUBT PLEASE CONSULT OUR TECHNICAL SUPPORT