



BLOCKWATER

Art. code see DDT

Date of issue 15.10.2010


Review nr. 01

Page 1 of 2

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

DESCRIPTION

Cementitious and ultra-quick set premixed mortar with special additives and aggregates to stop local water seepage, even under pressure. It can be used on mass concrete and masonry in general.



APPLICATION

Mix the product with water and hand apply with protection gloves by making a strong pressure for about 30 seconds.

TECHNICAL DATA

Aspect:	powder
Colour:	grey
Water:	17-18%
Specific weight:	1,65 gr/cm ³
Initial setting time:	about 40 seconds (20°C)
Final setting time:	about 90 seconds (20°C)
Max diameter aggregate particles:	0,5 mm
Mechanical resistances at compression after 28 days:	350 kg/cm ²

CONSUMPTION

1,5 kg/m² per mm of thickness.

PRECAUTIONS

Ensure that the application surfaces are free from greases and salts, clean and free from brittle parts. For a better result extend, if necessary, the dovetail hole.
Apply between +5° and +35°.

PACKAGING

5 kg bags – 4 pieces per box
25 kg bags – 60 bags per pallet

To the best of our knowledge, the information contained in this prospectus are correct and accurate, but every recommendation and suggestion is given without any guarantees, as the using conditions are not under our direct control. It is advisable to always perform some preliminary tests.
Our company reserves the right to modify the products and the content of this document without any warning.
The present edition annuls and replaces any other previous edition.

IN CASE OF DOUBT PLEASE CONSULT OUR TECHNICAL SUPPORT



BLOCKWATER

Art. code see DDT

Date of issue 15 10.2010

Review nr. 01

Page 2 of 2

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

STORAGE

The product has 12 months stability if properly packed and stored in a cool dry place. Store between +5° and +35°C.

SAFETY INSTRUCTIONS

PRECAUTIONS

For information about safety, user must refer to the most recent Safety Data Sheet, edited in accordance with the regulations in force, which contains physical, toxic and other data about the product in use.

ECOLOGY

Do not through out the product and/or empty containers in the environment. Consult the most recent Safety Data Sheet for further information about disposals.

To the best of our knowledge, the information contained in this prospectus are correct and accurate, but every recommendation and suggestion is given without any guarantees, as the using conditions are not under our direct control. It is advisable to always perform some preliminary tests.
Our company reserves the right to modify the products and the content of this document without any warning.
The present edition annuls and replaces any other previous edition.

IN CASE OF DOUBT PLEASE CONSULT OUR TECHNICAL SUPPORT